

Technical Datasheet

Items/ Unit / Test Method		Achilles Transparent Tarpaulin				
Product		E-1300F	E-1300FT	E-1300FS	SH-1300F	E-1300FK
Thickness		0,3mm	0,29mm	0,31mm	0,29mm	0,3mm
Width		203cm	203cm	203cm	203cm	203cm
Length		50m	50m	50m	50m	50m
Base Cloth		Polyester	Polyester	Polyester	Polyester	Polyester
Material		PVC	PVC	PVC	PVC	PVC
Weldable		Yes	Yes	Yes	Yes	Yes
Weight ±		405g/m2	395g/m2	425g/m2	385g/m2	410g/m2
Tensile strength [N/cm]	M.D.	298	288	305	283	276
	T.D.	268	261	275	271	251
Tear Strength [N]	M.D.	89	108.0	84	88.2	56.7
	T.D.	84.4	115.3	71.5	83	74.6
Characteristics		Fire Retardant	Fire Retardant	Fire Retardant	Fire Retardant	Fire Retardant
		(--)	Cold resistant	Antistatic	Heathshield	Antibacteria
Weather Resistance	800 hours	No major physical property change				

Product features
* Calendered
* Reach compliant
* Made in Japan
* Proven field performance
* Excellent weatherability (High & Low temperatures)
* Easy to clean
* UV stabilised - Little discolouration

M.D = MACHINE DIRECTION

T.D = TRANSVERSE DIRECTION

JIS = JAPANESE INDUSTRIAL STANDARD

Information stated on this Data Sheet is for reference purposes and is to the best of our knowlegde, true and reliable. Results cannot be guaranteed.